

NON-DESTRUCTIVE CONCRETE TESTING in STRUCTURES

Product Code

- UTC-3032 Original Schmidt Concrete Test Hammer
N Type (Proceq)
UTC-3040 Calibration Anvil

Standards

EEN 12504-2, 13791; ASTM C 805; BS 1881:202; NF P18-417;
DIN 1048; UNI 9189

The quality of concrete is mainly judged by its compressive strength directly affecting the load-bearing capacity and durability of concrete structures.

UTC-3032 Concrete Test Hammer (Original Schmidt Type N - Proceq) is used to measure the compressive strength characteristics of hardened concrete non-destructively, control uniform concrete quality and detect weak spots in the concrete. The test object should have a minimum thickness of 100 mm (3.9 in).

UTC-3040 Calibration Anvil, manufactured from a special steel alloy, is used for the calibration of concrete test hammers.

Product Code	Dimensions	Weight (approx.)
UTC-3032	340x120x120 mm	2 kg
UTC-3040	150x150x230 mm	16 kg
Measuring Range	10-70 N/mm ²	
Impact Energy	2.207 Nm	



UTC-3032



UTC-3040